



E 85115 A

Description



Powder



Printings

AJ-W65 ink is a tungsten ink suitable with aerosol jet printing.

Physical characteristics

Solvent	Organics
Solid content	60 - 70%
Particle size	< 100 nm
Viscosity	150 - 400 mPa.s
Resistivity	0.05 Ω/[]

Conditions of uses

Printing

- Aerosol Jet Printing

Cleaning

Excess ink can be removed with acetone, ethanol or IPA.

Preparation

-Ink requires planetary stirring before printing.

Storage

-Tightly sealed, leak-proof container on stirring
 -Storage at temperature <20°C
 -Storage up to 3 months

Drying & Curing

-Drying at ambient air
 -Sintering 60 min @ 1600°C under a reducing atmosphere (Ar/H₂)

Safety & Handling

Read the safety data sheet

Contact

products@cttc.fr
 7 rue Soyouz, 87068 LIMOGES, France
 +33 (0) 5.55.42.61.50, www.cttc.fr