


E 85115 A

Description



Powder



Printings

AJ-YSZ40 ink is a zirconia ink suitable with aerosol jet printing.

Physical characteristics

Solvent	Organics
Solid content	35 - 45%
Particle size	< 1.5 μm
Viscosity	150 - 200 mPa.s
Permittivity	To be measured

Conditions of uses

Printing

- Aerosol Jet Printing

Cleaning

Solvents such as ethanol, acetone or isopropanol.

Preparation

-Ink requires agitation before using

Storage

-Tightly sealed, leak-proof container on
-Stirring at temperature <20°C
-Storage up to 3 months

Drying & Curing

-Drying under atmospheric conditions
-Sintering 60 min @ 1200°C - 1400°C

Safety & Handling

Read the safety data sheet

Contact

products@cttc.fr

7 rue Soyouz, 87068 LIMOGES, France

+33 (0) 5.55.42.61.50, www.cttc.fr